

# Thermoplastic Unidirectional Tape PP GF 60-250 µm

Prod.No.

**Product description** Continuous glass fibre (GF) reinforced thermoplastic tape with unidirectional (UD) fibre orientation and a Polypropylen (PP) matrix in natural or black colour.

## Indicative values

Physical Properties	
<b>Glass Fibre Content</b>	60 %wt
<b>Fibre Areal Weight</b>	225 g/m <sup>2</sup>
<b>Fibre volume content</b>	35%
<b>Prepreg Areal Weight</b>	375 g/m <sup>2</sup>
<b>Nominal Thickness</b>	0,25 mm
<b>Available Widths</b>	3 mm to 300 mm

Thermal Properties	
<b>Melting Temperature</b>	165 °C
<b>Processing Temperature</b>	180 - 220 °C

Mechanical Properties	
<b>Tensile Strength</b>	720 MPa
<b>Tensile Modulous</b>	28 GPa
<b>Flexural Strength</b>	436 MPa
<b>Flexural Modulous</b>	21 GPa

**Storage /Handling:** This product must be stored at ambient temperatures, protected from sunlight and humidity. Shelf-life is not determined, we recommend to use within 12 months.

Note: The Information given above is based on our current state of knowledge and experience. In view of the many factors that may influence working conditions and the application of our products, the user is not relieved from carrying out his own tests and experiments. No legally binding warranty of certain properties or suitability for a particular purpose can be derived from this information. It is the responsibility of the receiver or user of our products to observe proprietary rights as well as existing laws and regulations. The latest version of the corresponding EU Safety Data Sheet must also be observed.

BÜFA Thermoplastic Composites GmbH & Co. KG  
 Stubbenweg 40  
 26125 Oldenburg  
 GERMANY  
 Phone +49 441 9317905  
 thermoplasticcomposites@buefa.de  
 www.buefa.de  
[www.thermoplasticcomposites.de](http://www.thermoplasticcomposites.de)

A member of the BÜFA-Group.