

# Thermoplastic Unidirectional Tape HDPE GF 66

Prod.No.

**Product description** Continuous glass fibre (GF) reinforced thermoplastic tape with unidirectional (UD) fibre orientation and a High Density Polyethylene (HDPE) matrix in natural or black colour.

## Indicative values

Physical Properties	
<b>Glass Fibre Content</b>	66 %wt
<b>Prepreg Areal Weight</b>	495 g/m <sup>2</sup>
<b>Nominal Thickness</b>	0,3 mm
<b>Available Widths</b>	3 mm to 635 mm

Thermal Properties	
<b>Melting Temperature</b>	135 °C
<b>Processing Temperature</b>	150 - 180 °C

Mechanical Properties	
<b>Tensile Strength</b>	880 MPa
<b>Tensile Modulus</b>	33 GPa

**Storage /Handling:** This product must be stored at ambient temperatures, protected from sunlight and humidity. Shelf-life is not determined, we recommend to use within 12 months.

Note: The Information given above is based on our current state of knowledge and experience. In view of the many factors that may influence working conditions and the application of our products, the user is not relieved from carrying out his own tests and experiments. No legally binding warranty of certain properties or suitability for a particular purpose can be derived from this information. It is the responsibility of the receiver or user of our products to observe proprietary rights as well as existing laws and regulations.

This product is an article according to Regulation (EC) Nr. 1907/2006 (REACH) and no substance or mixture. It requires no MSDS. Please conduct a risk assessment before processing, especially for working at melting or processing temperature or working with dust generation

BÜFA Thermoplastic Composites GmbH & Co. KG  
Stubbenweg 40  
26125 Oldenburg  
GERMANY  
Phone +49 441 9317905  
thermoplasticcomposites@buefa.de  
www.buefa.de  
[www.thermoplasticcomposites.de](http://www.thermoplasticcomposites.de)

A member of the BÜFA-Group.