

## Data Sheet

### Cordenka® 700 Super 3

	Linear Denisty (nominal)	Number of Filaments (nominal)	Linear Denisty	Breaking Force	Breaking Tenacity	Elongation at Break	Modulus
	Dtex		Dtex	N	Mpa	%	GPa
<b>Cordenka® 700</b>	1840	1000	1886	96.1	770	12.7	15.8
<b>Super 3</b>	2440	1350	2485	127.9	778	12.2	14.4
<b>Tensile Testing is performed at a conditioned yarn with a twist of Z100 t/m</b>							

Yarns of other linear densities are available on request.

All yarns are also available as chopped fibers with lengths between 2 mm and 125 mm.

### Shipment

Delivery forms				
Package Weight	Tube Dimension	Spool Ø	Spools per Pallet	Pallet Weight
	DtexL/Inner-Ø			
kg	mm	mm		kg
<b>4.3 (Z100 t/m)</b>	170/37.5	205	150	645
<b>5</b>	170/56	205	125	625
<b>10</b>	290/94	240	54	540

**Special instructions:**

- Notice the commercial weight
- store in a dry place
- only available with external trigger
- gentle handling and packaging