

# SKYi Stärk-OH1135

Technical Data Sheet: PP 30 LFT

## **Description:**

**SKYi Stärk-OH1135** is a special Heat stabilized long glass fibre reinforced polypropylene grade, for injection moulding and extrusion. The long glass fibres, chemically coupled to the polypropylene matrix, providing outstanding mechanical properties.

**SKYi Stärk-OH1135** is available both in black and natural. Other colours can be provided on request.

# **Applications:**

**SKYi Stärk-OH1135** is intended for injection moulding of highly demanding technical applications.

The excellent properties of **SKYi Stärk-OH1135** make it suitable for: Electrical components, automotive parts, interior, exterior and under the bonnet, structural furniture parts, load bearing, demanding components for various engineering sectors.

**SKYi Stärk-OH1135** can, in many of these applications, substitute other engineering plastics or metal alloys.

#### **Product Characteristics**

SR. NO.	PROPERTIES	TEST METHOD	UNITS	VALUES		
Α	PHYSICAL					
1	Specific gravity		g/cc	1.09		
В	MECHANICAL					
1	Tensile strength at break	ISO 527-I	MPa	110		
2	Tensile Modulus	ISO 527-I	MPa	6550		
3	Elongation at Break	ISO 527-I	%	2.3		
4	Flexural Strength	ISO 178	MPa	145		
5	Flexural Modulus	ISO 178	MPa	5800		
6	Charpy Impact Test- Notched	ISO 179-I	kJ/m²	19		
С	THERMAL					
1	HDT (At 0.45MPa)	ISO 75-I	٥C	160		

All Information supplied by or on behalf of SKYi composites in relation to its products, whether in the nature of data, recommendations or otherwise, is based on research and given in good faith, but SKYi composites assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to SKYi composites for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer. This certificate does not release the recipient from his obligation to carry out his usual incoming goods inspections. Our general conditions of sale remain in force.



# **Storage and Handling:**

**SKYi Stärk-OH1135** should be stored in dry conditions at temperatures below 50°C. Improper storage can initiate degradation with resulting odour generation and colour changes.

**Processing Guidelines:** TEMPERATURES- Barrel Zones

Material	Feed section (°C)	Nozzle(°C)	Melt temperature (°C)	Mold temperature (°C)
LFT GF-PP	220-230	230-250	230-250	80

#### Safety:

**SKYi Stärk-OH1135** is not classified as a dangerous preparation. Dust and fines from the product may give a risk for dust explosion. All equipment should be properly earthed. Inhalation of dust may irritate the respiratory system and should be avoided. During processing of the product small amounts of fumes are generated, which require proper ventilation.

## **Recycling:**

The product is suitable for recycling using modern methods of shredding and cleaning. Inhouse production waste should be kept clean to facilitate direct recycling. The Materials Safety Data Sheet is available on request. Please contact your SKYi representative for more details on various aspects of safety, recovery and disposal of the product.