

Thermoplastic Unidirectional Tape PP GF 70-250 µm

Prod.No.

Product description Continuous glass fibre (GF) reinforced thermoplastic tape with unidirectional (UD) fibre orientation and a Polypropylen (PP) matrix in natural or black colour.

Indicative values

Physical Properties	
Glass Fibre Content	70 %wt
Fibre Areal Weight	290 g/m ²
Fibre volume content	46 %
Prepreg Areal Weight	416 g/m ²
Nominal Thickness	0,25 mm
Available Widths	3 mm to 300 mm

Thermal Properties	
Melting Temperature	165 °C
Processing Temperature	180 - 220 °C

Mechanical Properties	
Tensile Strength	940 MPa
Tensile Modulus	35 GPa
Flexural Strength	610 MPa
Flexural Modulus	34 GPa

Storage /Handling: This product must be stored at ambient temperatures, protected from sunlight and humidity. Shelf-life is not determined, we recommend to use within 12 months.

Note: The Information given above is based on our current state of knowledge and experience. In view of the many factors that may influence working conditions and the application of our products, the user is not relieved from carrying out his own tests and experiments. No legally binding warranty of certain properties or suitability for a particular purpose can be derived from this information. It is the responsibility of the receiver or user of our products to observe proprietary rights as well as existing laws and regulations.

This product is an article according to Regulation (EC) Nr. 1907/2006 (REACH) and no substance or mixture. It requires no MSDS. Please conduct a risk assessment before processing, especially for working at melting or processing temperature or working with dust generation

BÜFA Thermoplastic Composites GmbH & Co. KG
Stubbenweg 40
26125 Oldenburg
GERMANY
Phone +49 441 9317905
thermoplasticcomposites@buefa.de
www.buefa.de
www.thermoplasticcomposites.de

A member of the BÜFA-Group.